

論文 / 著書情報  
Article / Book Information

題目(和文)	超伝導渦糸系における非平衡現象と相転移
Title(English)	Non-equilibrium Phenomena and Phase Transitions in Superconducting Vortex Systems
著者(和文)	河村泰樹
Author(English)	Yasuki Kawamura
出典(和文)	学位:博士(理学), 学位授与機関:東京工業大学, 報告番号:甲第10060号, 授与年月日:2016年3月26日, 学位の種別:課程博士, 審査員:大熊 哲,吉野 淳二,藤澤 利正,笹本 智弘,竹内 一将
Citation(English)	Degree:Doctor (Science), Conferring organization: Tokyo Institute of Technology, Report number:甲第10060号, Conferred date:2016/3/26, Degree Type:Course doctor, Examiner:,,,,
学位種別(和文)	博士論文
Category(English)	Doctoral Thesis
種別(和文)	論文要旨
Type(English)	Summary

# 論文要旨

THESIS SUMMARY

専攻： 物性物理学 専攻  
Department of  
学生氏名： 河村 泰樹  
Student's Name

申請学位 (専攻分野)： 博士 (理学)  
Academic Degree Requested Doctor of  
指導教員 (主)： 大熊 哲  
Academic Advisor(main)  
指導教員 (副)： 吉野 淳二  
Academic Advisor(sub)

要旨 (英文 800 語程度)  
Thesis Summary (approx.800 English Words)

In this thesis, first, I report experimental studies on fast driven vortex lattices in Corbino disk (CD) subject to shear forces, focusing on a change in the coherence of lattices by changing a drive velocity or effective pinning. Then, I present critical dynamics of individual vortices associated with dynamic ordering near the non-equilibrium phase transitions observed in the low velocity region. Samples used in this work are uniform amorphous  $\text{Mo}_x\text{Ge}_{1-x}$  films with weak pinning. Through this thesis, I demonstrate that the superconducting vortices are a very suitable system to study the physics of plastic flow and novel non-equilibrium phenomena.

In earlier work, our group found the formation of rotating vortex rings composed of triangular arrays in CD by means of a mode-locking (ML) resonance. However, information on the transverse dynamic correlations, namely, the width of the lattice rings remains unresolved. This information is indispensable to understanding the physics of plastic flow. In this thesis, I perform precise measurements of dc current-voltage ( $I - V$ ) relation for the lattice rings rotated by dc  $I$  superimposed with ac current  $I_{rf}$  in CD. With increasing  $I_{rf}$ , the ML resonance becomes more pronounced and  $I - V$  curves at large  $I$  show a trend to decrease. This is opposite to the generally accepted behavior of vortex flow, where  $I_{rf}$ -induced depinning results in an increase in a flux-flow voltage. The observed peculiar behavior is explained by the  $I_{rf}$ -induced growth in the width of the rotating lattice rings.

Using the periodically sheared vortex system in CD, our group offered evidence of a reversible-irreversible transition (RIT), as originally reported in a driven colloidal system. By increasing a displacement  $d$  of vortices per cycle, a threshold displacement  $d(\equiv d_{c1})$  for RIT was determined as an onset of flow noise  $S_V$ . The amplitude of time-dependent voltage  $|V(t)|$  exhibited a gradual increase toward a steady-state value, indicative of dynamic ordering, and a relaxation time  $\tau$  shows a power-law divergence at  $d_{c1}$ . Here, to obtain information about the vortex configuration near the RIT, I perform comparative measurements of  $V(t)$  generated by ac drive, focusing on how the initial vortex configuration in CD affects the transient vortex dynamics. It is found that when the initial vortex configuration is disordered or prepared by freezing the irreversible flow, the increase in  $|V(t)|$  toward the steady state indicative of random organization is visible. In contrast, when the initial configuration is ordered or prepared by freezing reversible flow, only a fast decay in  $V(t)$  coming from dynamic disordering is observed. The obtained results seem qualitatively consistent with the general theoretical view that the irreversible vortex motion occurs in correspondence with the flow of topological defects in the vortex lattice.

I extend the measurements of  $S_V$  to a much larger  $d$  regime and find the second characteristic displacement  $d_{c2}$  in addition to  $d_{c1}$ . This  $d_{c2}$  is a new length scale characterizing the phenomenon associated with RIT and is interpreted as a displacement separating the completely irreversible regime, where all flow channels are irreversible ( $d > d_{c2}$ ), from the coexistence regime composed of irreversible and reversible flow channels ( $d_{c1} < d < d_{c2}$ ).

I note that experimental evidence of RIT has been obtained only in colloidal and vortex systems where a global shear inversely proportional to a radius is present. Here, I conduct an experiment of RIT in strip samples where only a local shear due to random pinning centers is present. We again obtain evidence of RIT with a critical behavior similar to that for CD, consistent with the theoretical prediction. I also find the critical behavior similar to that of RIT for the same vortex system in the strip samples driven by superimposed ac and dc forces. Seen in the moving frame driven with a dc velocity, the “reversible” phase is enlarged and a relaxation time to the steady state is significantly suppressed. They are explained by the weakened effective pinning strength due to the dc velocity. I find an unexpected suppression of critical exponents from  $\nu = 1.4$  in the rest frame to 0.7 in the moving frame. I propose two possible interpretations based on RIT with different pinning properties and on a novel dynamic transition characterized by  $\nu = 0.7$ .

Finally, I study a general phenomenon of plastic depinning using the same vortex system, focusing on whether the critical behavior near the dc depinning transition found in our group is also observed for the ac drive. The results show that the critical behavior of the depinning transition is commonly observed for the ac drive. The critical exponents for the dc and ac depinning transitions are around  $\nu = 1.4$ , which are close to the ones obtained in RIT. These results are consistent with the theoretical prediction that the RIT and the plastic depinning transition may fall into the same universality class as the absorbing transition.

備考：論文要旨は、和文 2000 字と英文 300 語を 1 部ずつ提出するか、もしくは英文 800 語を 1 部提出してください。

Note: Thesis Summary should be submitted in either a copy of 2000 Japanese Characters and 300 Words (English) or 1 copy of 800 Words (English).

注意：論文要旨は、東工大リサーチリポジトリ(T2R2)にてインターネット公表されますので、公表可能な範囲の内容で作成してください。  
Attention: Thesis Summary will be published on Tokyo Tech Research Repository Website (T2R2).