

論文 / 著書情報
Article / Book Information

題目(和文)	LiCoO ₂ /Li ₁₀ GeP ₂ S ₁₂ ならびにTiS ₂ /Li ₁₀ GeP ₂ S ₁₂ 複合体電極の作製と全固体電池特性
Title(English)	Fabrication and electrochemical properties of LiCoO ₂ /Li ₁₀ GeP ₂ S ₁₂ and TiS ₂ /Li ₁₀ GeP ₂ S ₁₂ composite electrodes for all solid-state batteries
著者(和文)	LIWEN JING
Author(English)	Wen Jing Li
出典(和文)	学位:博士(工学), 学位授与機関:東京工業大学, 報告番号:甲第10193号, 授与年月日:2016年3月26日, 学位の種別:課程博士, 審査員:菅野 了次,平山 雅章,大坂 武男,北村 房男,中村 二郎
Citation(English)	Degree:., Conferring organization: Tokyo Institute of Technology, Report number:甲第10193号, Conferred date:2016/3/26, Degree Type:Course doctor, Examiner:,,,,,
学位種別(和文)	博士論文
Category(English)	Doctoral Thesis
種別(和文)	論文要旨
Type(English)	Summary

(博士課程)
Doctoral Program

論文要旨

THESIS SUMMARY

専攻 : Department of	物質電子化学	専攻	申請学位 (専攻分野) : Academic Degree Requested	博士 (工学)
学生氏名 : Student's Name	Li Wenjing		指導教員 (主) : Academic Advisor(main)	菅野了次
			指導教員 (副) : Academic Advisor(sub)	平山雅章

要旨 (英文 800 語程度)

Thesis Summary (approx.800 English Words)

Development of all solid-state lithium batteries has been anticipated to address safety issues of conventional lithium-ion batteries when applied for large-scale devices. In this thesis, $\text{Li}_{10}\text{GeP}_2\text{S}_{12}$ (LGPS) with high lithium ion conductivity of 12 mS cm^{-1} was selected as the solid electrolyte. Two kinds of the composite cathodes were prepared by mixing the LGPS with the LiNbO_3 -coated LiCoO_2 or TiS_2 cathode active materials. The mixing condition, processes for the composite cathodes and electrochemical properties were investigated to suppress the interfacial resistance between the electrode and electrolyte by increasing the contact area.

For the $\text{LiCoO}_2/\text{LGPS}$ system, the composite cathode LiNbO_3 -coated LiCoO_2 and LGPS were mixed with a weight ratio of 70:30 by a mill pot rotator. The fabrication conditions were mix speed, mix time and particle size of the LGPS. The LiNbO_3 was selected as coating material to decrease the interfacial resistance. The composite electrodes were characterized by scanning electron microscopy and X-ray diffractometry. Highly dispersed composites of $\text{LiCoO}_2/\text{LGPS}$ were successfully obtained by mild grinding applying a mill pot rotation rate of 140 rpm for 30 min with 3 mm ϕ agate balls. the LGPS particle size of 2 μm and LiNbO_3 coating layer thickness of 5.8 nm. The composite cathode prepared with 5.8 nm-coated LiCoO_2 and 2 μm LGPS powders exhibited the first discharge capacity of 124 mAh g^{-1} when operating at a current density of 7 mA g^{-1} . However, the discharge capacity gradually decreased with the cycle number. Electrochemical impedance spectroscopy analysis clarified that the capacity fading was primarily caused by the increase in the resistance to lithium diffusion at the In-Li anode/the LGPS electrolyte interface. The LGPS electrolyte could be decomposed by the contact to the In-Li anode due to instability at low potential regions. Modification of the In-Li/LGPS interface is needed to stabilize the interface for improving the cycle stability of the batteries.

For the TiS_2/LGPS system, composite cathodes were prepared using a vortex miller at 2500 rpm for 10 min with a weight ratio between TiS_2 and LGPS of 30:70. A $\text{TiS}_2/\text{Li}_{10}\text{GeP}_2\text{S}_{12}/\text{In-Li}$ cell with nano-size TiS_2 (particle size 200~500 nm) showed the first discharge capacity 239 mAh g^{-1} . However, the discharge capacity rapidly decreased even at low current density of 0.05 C. As the lithiated LiTiS_2 has a considerably larger lattice volume (64.1 \AA^3) than the TiS_2 (57.1 \AA^3), the physical contact between the TiS_2 and the LGPS could be deteriorated by the large volume change during

lithiation/delithiation processes. To clarify the influence of the volume change on the cycle stability, the charge-discharge measurements were operated with an applying pressure of 230 MPa. The first discharge capacity was 200 mAh g⁻¹ at a current density of 1 C, and the discharge capacity was maintained at 168 mAh g⁻¹ in the initial ten cycles. Furthermore, the capacity at 5 C was half of that at 1 C, which is much better than that of a cell under no pressure. The severe cycle retention and rate capability were greatly improved in the batteries operated with an applying pressure of 230 MPa. Eliminating the volume change of the composite electrodes is important for achieving stable battery operation and performance.

The charge-discharge reactions can proceed in all-solid state batteries with composite powder cathodes of the LiNbO₃-coated LiCoO₂/LGPS and TiS₂/LGPS. Synthesis conditions of the composite cathodes considerably affect the charge-discharge capacity, cycle retention, and rate-capability of all-solid-state batteries. For the further improvement, search for suitable coating layer material and decrease the anode/LGPS interfacial resistance are key factors for the batteries with the oxide cathodes. For the sulfide cathode, eliminating the volume change of the composite electrodes is important for achieving the stable battery operation and performance.

備考：論文要旨は、和文 2000 字と英文 300 語を 1 部ずつ提出するか、もしくは英文 800 語を 1 部提出してください。

Note: Thesis Summary should be submitted in either a copy of 2000 Japanese Characters and 300 Words (English) or 1 copy of 800 Words (English).

注意：論文要旨は、東工大リサーチリポジトリ(T2R2)にてインターネット公表されますので、公表可能な範囲の内容で作成してください。

Attention: Thesis Summary will be published on Tokyo Tech Research Repository Website (T2R2)