

論文 / 著書情報
Article / Book Information

題目(和文)	岩塩・ペロブスカイト・逆蛍石型構造を有する酸化物系リチウムイオン導電体の合成、構造と電気化学特性
Title(English)	Synthesis, structures and electrochemical properties of lithium ion conducting oxides with rock-salt, perovskite and anti-fluorite structures
著者(和文)	趙国偉
Author(English)	Guowei Zhao
出典(和文)	学位:博士(理学), 学位授与機関:東京工業大学, 報告番号:甲第10427号, 授与年月日:2017年3月26日, 学位の種別:課程博士, 審査員:菅野 了次,平山 雅章,川路 均,北村 房男,松下 伸広,中村 二郎
Citation(English)	Degree:Doctor (Science), Conferring organization: Tokyo Institute of Technology, Report number:甲第10427号, Conferred date:2017/3/26, Degree Type:Course doctor, Examiner:,,,,,
学位種別(和文)	博士論文
Category(English)	Doctoral Thesis
種別(和文)	論文要旨
Type(English)	Summary

(博士課程)
Doctoral Program

論文要旨

THESIS SUMMARY

専攻 : Department of	物質電子科学	専攻	申請学位 (専攻分野) : Academic Degree Requested	博士 (理学)
学生氏名 : Student's Name	趙国偉 (Guowei ZHAO)		指導教員 (主) : Academic Advisor(main)	菅野了次
			指導教員 (副) : Academic Advisor(sub)	平山雅章

要旨 (英文 800 語程度)

Thesis Summary (approx.800 English Words)

Chapter 1: In this thesis, novel lithium ion conducting oxides were developed using reported structural frameworks, rock-salt, perovskite, and anti-fluorite-types. Base compositions for these structures are LiScO_2 , $(\text{Li}_x\text{La}_{1-x/3})\text{ScO}_3$, and $\text{Li}_{5+x}(\text{Fe}_{1-x}\text{Zn}_x)\text{O}_4$, respectively. Aliovalent cation doping to improve lithium ion conductivity was examined for LiScO_2 and $(\text{Li}_x\text{La}_{1-x/3})\text{ScO}_3$. These oxide-based materials were synthesized by ambient pressure or high-pressure synthesis method to obtain target composition and structure. Structure analysis and electrochemical evaluation were conducted to understand their relationship and achieve further improvements in the electrochemical properties of the lithium ion conductors.

Chapter 2: The powder samples were synthesized by either solid-state reaction in air at 900–1350°C (Chapter 3, LiScO_2 system), 650–750°C (Chapter 5, Li_5FeO_4 anti-fluorite system) or high-pressure synthesis method at 900–1250 °C with a pressure of 1–2 GPa (Chapter 4, LaScO_3 perovskite system). Obtained samples were subjected to X-ray and synchrotron X-ray diffraction analyses for structure determination. Diffraction data was analyzed by Rietveld refinement method using Rietan-FP program. Ionic conductivity was measured by the AC-impedance method using frequency response analyzers (Solartron 1260); the samples were placing under flowing Ar gas, and the measurements were performed over the temperature range from 25 to 450 °C and the frequency range from 0.1 Hz to 10 MHz. Gold pastes were painted onto both sides of each sample for the measurements as the blocking electrodes.

Chapter 3: The lithium containing oxides, rock-salt type LiScO_2 and $\text{Li}_{1-y}\text{Sc}_{1-x}\text{M}_x\text{O}_2$ ($M = \text{Zr}^{4+}$, Nb^{5+} and Ta^{5+}) were synthesized. The highest conductivity of $7.94 \times 10^{-6} \text{ S cm}^{-1}$ at 350 °C for the sample doped with 10% Zr^{4+} was confirmed, which was improved by two orders of magnitude than that of LiScO_2 . Enhanced ionic conductivities were achieved by the introduction of vacancies in the structure by doping with tetra-valent cations (Zr^{4+}) at Sc-site.

Chapter 4: The perovskite type $(\text{Li}_x\text{La}_{1-x/3})\text{ScO}_3$ and M -doped $(\text{Li}_x\text{La}_{1-x/3})\text{ScO}_3$ ($M = \text{Ce}^{4+}$, Zr^{4+} , Nb^{5+}) were synthesized and their lithium ion conductive properties were investigated. A -site doping ($M = \text{Ce}^{4+}$) improved the conductivity of $(\text{Li}_x\text{La}_{1-x/3})\text{ScO}_3$, while the presence of B -site doping ($M = \text{Zr}^{4+}$, Nb^{5+}) did not contribute its improvement. An optimal compound $(\text{Li}_{0.4}\text{Ce}_{0.15}\text{La}_{0.67})\text{ScO}_3$ shows the maximum ionic conductivity of $1.06 \times 10^{-3} \text{ S cm}^{-1}$ at 350 °C, which is nearly two orders of magnitude improved comparing to that of the optimal composition $(\text{Li}_{0.45}\text{La}_{0.85})\text{ScO}_3$ in $(\text{Li}_x\text{La}_{1-x/3})\text{ScO}_3$ system. The crystal structure analyses and ionic conductivity measurements indicate the ionic conductivities of $(\text{Li}_x\text{La}_{1-x/3})\text{ScO}_3$ could be improved because

of the introduction of lithium-ion and lithium-ion interstitials in the structure by doping with a tetra-valent cation (Ce^{4+}) at A^{3+} -site.

Chapter 5: $\text{Li}_{5+x}(\text{Fe}_{1-x}\text{Zn}_x)\text{O}_4$ forms solid solutions in $0 \leq x \leq 0.1$ and $0.1 < x \leq 1$ for α - and β -phases, respectively. The phases are reported to be obtained by quenching process. However, a dominant factor in determining the conductivity and conductivity jumped at high temperature region (~ 430 °C) are still unclear. To solve these problem and obtain a direction of novel material design, $\text{Li}_{5+x}(\text{Fe}_{1-x}\text{Zn}_x)\text{O}_4$ are investigated in this chapter. $\text{Li}_{5+x}(\text{Fe}_{1-x}\text{Zn}_x)\text{O}_4$ formed solid solutions in $0 \leq x \leq 0.3$ and $0.5 \leq x \leq 1$ for α - and β -phases, respectively by a solid state synthesis method with a slow cooling process. The α -phase obtained in this study, $\text{Li}_{5+x}(\text{Fe}_{1-x}\text{Zn}_x)\text{O}_4$ ($x = 0.2, 0.3$) showed lower ionic conductivity than reported β -phase with the same composition. The fact indicates the phase-type is the dominant factor for higher ionic conductivity than the composition. The formation of LiOH by a decomposition of this material due to reaction with water in the atmosphere was detected, indicating the conductivity jump is contributed to the liquid phase of LiOH at the high-temperature. High-temperature β -phase with anti-fluorite structure could be good candidates as solid electrolyte while controlling the atmosphere is required for this material.

Chapter 6: In this chapter, the conclusion of this study is mentioned. The ionic conductivities of rock-salt type LiScO_2 and perovskite-type LaScO_3 -based materials were improved by doping of lithium vacancy or interstitial, respectively. Optimizing the solid solution formation region with suitable doping/substitution elements and synthesis methods, and understanding the conductive mechanism and structure characteristics of the materials are valuable knowledge for developing new groups of solid lithium ion conductors that can be used in practical applications as solid electrolytes or electrodes for all-solid-state lithium batteries.

備考：論文要旨は、和文 2000 字と英文 300 語を 1 部ずつ提出するか、もしくは英文 800 語を 1 部提出してください。

Note : Thesis Summary should be submitted in either a copy of 2000 Japanese Characters and 300 Words (English) or 1copy of 800 Words (English).

注意：論文要旨は、東工大リサーチリポジトリ(T2R2)にてインターネット公表されますので、公表可能な範囲の内容で作成してください。

Attention: Thesis Summary will be published on Tokyo Tech Research Repository Website (T2R2).