T2R2 東京科学大学 リサーチリポジトリ Science Tokyo Research Repository

論文 / 著書情報 Article / Book Information

題目(和文)			
Title(English)	Metallization and Functionalization of Flexible Silk Textile by Supercritical CO2 Promoted Electrochemical Techniques		
著者(和文)	Chiu Wan-Ting		
Author(English)	Wan-Ting Chiu		
出典(和文)	学位:博士(工学), 学位授与機関:東京工業大学, 報告番号:甲第10980号, 授与年月日:2018年9月20日, 学位の種別:課程博士, 審査員:曽根 正人,寺田 芳弘,木村 好里,細田 秀樹,三宮 工		
Citation(English)	Degree:Doctor (Engineering), Conferring organization: Tokyo Institute of Technology, Report number:甲第10980号, Conferred date:2018/9/20, Degree Type:Course doctor, Examiner:,,,,		
学位種別(和文)			
Category(English)	Doctoral Thesis		
種別(和文)	 論文要旨 		
Type(English)	Summary		

論文要旨

THESIS SUMMARY

専攻: Department of	材料物理科学	専攻	申請学位(専攻分野): 博士 (工学)	
 学生氏名:	Chiu Wan-Ting		指導教員(主):	
Student's Name			Academic Supervisor(main) 冒根 止入	
			指導教員(副): 寺田 芳弘	
			Academic Supervisor (sub)	

要旨(和文 2000 字程度)

Thesis Summary (approx.2000 Japanese Characters)

Metallization and functionalization of textile materials are important topics toward the applications of wearable devices such as bio-sensor and e-clothing. The integration of the distinct materials such as polymer, metal, and oxides becomes the greatest challenge. Electroless plating is a promising technique to combine metal materials and non-electrically conductive polymer substrate together. This technique can especially be applied to the substrate with sophisticated structures such as textile. Electroless plating is divided into three major steps, pretreatment is the first step to clean and roughen the substrate, catalyzation is the second step to embed the catalysts into the substrate making the substrate active, and the final step is metallization step to metallize the substrate. In the conventional catalyzation step, the catalysts were only inlaid on the substrate surface due to the polar property of aqueous solution. Supercritical carbon dioxide (sc-CO₂) was introduced into the catalyzation step to solve the aforementioned problems. Since sc-CO₂ owns both the properties of gas and liquid phases, affinity to non-polar material, non-corrosive to most of the polymers, and low surface tension, it thus can bring the non-polar metal-organic complex catalysts (i.e. Palladium(II) acetylacetonate) to go into the polymer substrate and remains the substrate undamaged. In this way, the adhesion between polymer substrate and deposited materials can be improved due to embedment of the catalysts into the substrate. On the other hand, sc-CO₂ can also be introduced into the metallization step to enhance the metallization properties. There are usually hydrogen evolutions during the metallization and the hydrogen bubbles might be embedded into the metallization layer resulting in the defects in the metallization layer. With the help of sc-CO₂ micelle bouncing in the solution, it can carry the H₂ bubbles away and reduce the defects in the metallization layer. Therefore, sc-CO₂ promoted electroless plating (i.e. sc-CO₂ catalyzation and sc-CO₂ metallization) was carried out for the integration of metal and textile materials.

Silk textile, a common cloth material, was chosen in this study on account of its flexibility and stitchability. Ni–P was chosen due to its highly electrical conductivity, high

corrosion resistance, and high wear resistance. However, Ni shows allergic issue, Pt and Au were thus chosen to solve the biocompatibility problems. In the meanwhile, Pt and Au also own the highly electrical conductivity, high corrosion resistance, and high wear resistance. In this study, metallization layers of Ni–P, Pt, and Au were integrated with silk textile by the sc–CO₂ promoted electroless plating to achieve the composites toward the applications of flexible wearable devices.

In the meanwhile, the wearable devices are required to be equipped with different functions such as the photovoltaic and photocatalytic devices in response to the requirements of the next–generation technology. There are many materials that can play the role as the photocatalyst in the composite material, such as TiO_2 , CuO, and ZnO. ZnO and TiO_2 were chosen for the photocatalytic materials due to their proper band gap energies and low cost. ZnO and TiO_2 were fabricated on the metallized silk textile by the cathodic deposition and co–deposition methods to fulfill the requirements of photocatalytic properties.

The surface morphology, cross–section, and compositions of the silk/metal/oxide composites were examined by an OM, SEM, and EDX. The crystal structures and phases were identified by an XRD. Electrical resistances were evaluated by a four–point probe. Electrical resistance was measured again after the adhesive test conducted by the tape paste/peel–off tests for evaluating the adhesive firmness of the composites. Corrosion resistances were measured by the polarization method in 3.5 wt.% NaCl and simulated body fluid (SBF), respectively. 3.5 wt.% NaCl was for simulating human sweat and SBF was for simulating human body fluid. Biocompatibility was evaluated by the immersion test in the SBF solution. The evaluation of photocatalytic activities were conducted in a three–electrode cell consisting of a Pt counter electrode, Ag/AgCl reference electrode, and a piece of the silk/metal/oxides as the working electrode. The evaluation processes were carried out at room temperature and 1 atm. 0.5 M Na₂SO₄ solution was used as the electrolyte.

Metallized silk textile with proper electrical resistance ranges were fabricated for the applications of wearable devices. The composites show firmly adhesive properties after adhesive tests. Processed silk showed the high corrosion resistances in both 3.5 wt.% NaCl and SBF solutions. Metallized silk textile equipped with ZnO or TiO₂ showed the high photocatalytic activity.

備考:論文要旨は、和文2000字と英文300語を1部ずつ提出するか、もしくは英文800語を1部提出してください。

Note : Thesis Summary should be submitted in either a copy of 2000 Japanese Characters and 300 Words (English) or 1copy of 800 Words (English).

注意:論文要旨は、東工大リサーチリポジトリ(T2R2)にてインターネット公表されますので、公表可能な範囲の内容で作成してください。 Attention: Thesis Summary will be published on Tokyo Tech Research Repository Website (T2R2).