T2R2東京工業大学リサーチリポジトリ Tokyo Tech Research Repository

論文 / 著書情報 Article / Book Information

論題(和文)	
Title(English)	Gas Species Comparison of Fast Atom Beam Irradiation to Photoluminescence Properties of GaInAs/InP layers for Surface Activated Bonding
著者(和文)	
Authors(English)	Yuning Wang, Takuya Mitarai, Tomohiro Amemiya, Nobuhiko Nishiyama, Shigehisa Arai
出典	
	18a-232-9
	2018, 9

Gas Species Comparison of Fast Atom Beam Irradiation to Photoluminescence Properties of GaInAs/InP layers for Surface Activated Bonding

Yuning Wang¹, Takuya Mitarai¹, Tomohiro Amemiya^{1,2}, Nobuhiko Nishiyama^{1,2}, and Shigehisa Arai^{1,2} Department of Electrical and Electronic Engineering¹,

Department of Electrical and Electronic Engineering,

Laboratory for Future Interdisciplinary Research of Science and Technology²

Tokyo Institute of Technology

E-mail: wang.y.bf@m.titech.ac.jp

1. Introduction

Hydrophilic bonding or plasma activated bonding (PAB) [1,2] are usually used for hybrid wafer bonding. However, to achieve high bonding strength, annealing temperature of higher than 150° C, resulting in the thermal stress caused by the difference between thermal expansion coefficients of bonded wafers, and long cooling time are required. To deal with the mentioned problems, surface activated bonding (SAB) based on fast atom beam (FAB) [3] was proposed in recent years, which can realize wafer bonding at room temperature. In our previous report, we reported the influence of Ar-FAB to photoluminescence properties of GaInAs/InP wafers [4]. In this report, we assessed the influence by other gases N₂ and Xe.

2. Experiment Results

In this experiment, depth dependence of wafer damage after FAB irradiation was evaluated by photoluminescence (PL) intensity degradation. Only one wafer put on lower side of the SAB equipment is irradiated by FAB. The layer structure of the evaluated wafer is shown in Fig. 1. The wafer consists of 4 GaInAs quantum wells (QWs) with different thickness (emit at different wavelength) separated with 200-nm InP. Fig. 2 shows the normalized PL intensity of 3-nm thick GaInAs (50-nm quantum well depth) as a function of irradiation time for Ar-FAB, Xe-FAB, and N2-FAB sources at different FAB currents. PL intensity was decreased by FAB irradiation even the irradiation time was short. The degradation is smaller at lower FAB current at the same irradiation time. This means low FAB current should be utilized in wafer bonding in order to keep PL property, although too low current cannot make activated surface and bond the wafers. Fig. 3 shows quantum well depth dependence of normalized PL intensities under the irradiation time and current of 10 sec. and 5 mA, respectively. It was found that normalized PL intensity kept >80% at 450-nm quantum well depth under low current and short irradiation time for three FAB sources. Meanwhile, Xe-FAB resulted in the less degradation under the same FAB conditions (current and irradiation time) compared with Ar-FAB and N2-FAB. One of the explanation may be related to that the atomic mass of Xe is bigger than those of Ar and N. For the future plan, we need to investigate more FAB sources, such as Kr and Ne to figure out the reason of the degradation of normalized PL intensity and choose the most suitable FAB sources for InP/Si wafer bonding.

Acknowledgment

This work was financially supported by NEDO, JST-ACCEL (JPMJAC1603), JST-CREST (JPMJCR15N6), JSPS KAKENHI Grant Numbers (#15H05763, #16H06082, #15J11774, #17H03247).



References

- [1] A. W. Fang, et al., Opt. Express 14, 9203 (2006).
- [2] Y. Hayashi, et al., JJAP 55, 082701 (2016).
- [3] G. Kono, et al., ICEP 2014, Proc. FE3-5, 720 (2014).
- [4] K. Nagasaka, et al., JJAP 78, 7a-A504-11 (2018).