

論文 / 著書情報  
Article / Book Information

題目(和文)	
Title(English)	Corrosion-reconstruction bonding of freestanding ultrathin glass film on metal at room temperature
著者(和文)	LiuYin
Author(English)	Yin Liu
出典(和文)	学位:博士(学術), 学位授与機関:東京工業大学, 報告番号:甲第11655号, 授与年月日:2020年9月25日, 学位の種別:課程博士, 審査員:矢野 哲司,松下 伸広,生駒 俊之,小林 郁夫,林 幸
Citation(English)	Degree:Doctor (Academic), Conferring organization: Tokyo Institute of Technology, Report number:甲第11655号, Conferred date:2020/9/25, Degree Type:Course doctor, Examiner:,,,,
学位種別(和文)	博士論文
Category(English)	Doctoral Thesis
種別(和文)	論文要旨
Type(English)	Summary

## 論文要旨

THESIS SUMMARY

系・コース： Department of, Graduate major in	材料 材料	系 コース	申請学位(専攻分野)： Academic Degree Requested	博士 Doctor of	( 学術 )
学生氏名： Student's Name	LIU YIN		指導教員(主)： Academic Supervisor(main)	矢野 哲司 教授	
			指導教員(副)： Academic Supervisor(sub)	松下 伸広 教授	

要旨 (英文 800 語程度)

Thesis Summary (approx.800 English Words )

In this thesis, a room temperature glass coating technique, corrosion-reconstruction bonding, with simple process on metal by using freestanding ultrathin glass film as coating materials and using water as bonding agent is developed. Two points are focused in this thesis: firstly, 45S5 bioactive freestanding ultrathin glass films are prepared and used to develop this glass coating technique, investigate the bonding mechanism, and indicate the potential application; secondly, the effect of glass composition on the bonding behavior, which helps to find the proper glass composition for strong bonding in the corrosion-reconstruction bonding, is investigated.

In chapter 2, a simple glass coating method on metal by using ultrathin glass films as coating materials and water as bonding agent was developed. 45S5 bioactive freestanding ultrathin glass films were prepared by the glass blowing technique. Ultrathin glass films with thickness of 1 to 5  $\mu\text{m}$  could be obtained, and then be bonded on a polished Ti plate at room temperature with a water layer between them. The glass films bonded strongly on Ti plate surface, and the bonding strength increased when the bonded sample is stored in ambient atmosphere at room temperature. The bonding strength was about 370  $\text{mJ}/\text{m}^2$  after bonding and increased up to about 900  $\text{mJ}/\text{m}^2$  after 9-hours bonding. This result indicates a simple room temperature glass coating technique is successfully developed.

In chapter 3, the bonding mechanism between 45S5 glass films and Ti plate at room temperature shown in chapter 2 was investigated in detail. The 45S5 ultrathin glass films prepared by glass blowing technique were found containing surface  $\text{Na}_2\text{O}$ -rich layer. The bonding mechanism between the 45S5 glass films and Ti plate was clarified by the XPS and TEM results as a corrosion-reconstruction bonding. This mechanism contains four steps: step 1, glass films and Ti plate bonds together by hydrogen bond of water layer; step 2, ion exchange of  $\text{Na}^{2+} \leftrightarrow \text{H}^+$  between glass film and water layer occurs which forms a high pH solution in the bonding interface; step 3, surface of glass films and Ti plate corrodes by the high pH solution to form a bonding interfacial layer; step 4, the formed bonding interfacial layer polymerizes to induce a strong bonding during the storage process of the bonded sample. These steps occur fast after bonding, which is the reason for the much higher bonding strength after bonding (370  $\text{mJ}/\text{m}^2$ ) than the hydrogen bonds ( $\sim 100 \text{mJ}/\text{m}^2$ ).

In chapter 4, a 45S5 multi-layer structure was constructed by using the corrosion-reconstruction bonding for potential applications. 45S5 ultrathin glass films could bonded together strongly, their bonding strength also increased when the bonded samples were stored in ambient atmosphere at room temperature. The bonding strength was similar to that of the glass films on Ti plate, which means that the increase of the bonding strength after storage was due to the polymerization of the silicate components in the bonding interfacial layer. These results indicate that multi-layer structure of ultrathin glass films on substrate, in which a multi-function could also be potential by changing glass films, could be constructed by the corrosion-reconstruction bonding method at room temperature for potential applications.

In chapter 5, the effect of glass composition on the surface of ultrathin glass films was investigated. As shown in chapter 3, the surface  $\text{Na}_2\text{O}$ -rich layer on glass films was important for the strong bonding on Ti plate, the observation of glass compositions which could induce this surface  $\text{Na}_2\text{O}$ -rich layer was focused. Several glasses based on the soda-lime-silicate (including a magnesium-lime-silicate glass) and soda-lime-phosphate glasses were chosen, and corresponding ultrathin glass films were also prepared by glass blowing technique. Freestanding ultrathin glass films could be all prepared from these glasses. The surface  $\text{Na}_2\text{O}$ -rich layer was observed in soda-lime-silicate glass films with glass composition of  $\text{SiO}_2 < 62.5 \text{ mol}\%$ ,  $\text{CaO} < 25 \text{ mol}\%$ , and  $\text{Na}_2\text{O} \geq 25 \text{ mol}\%$  within the glass-forming region. The other compositions among the glass-forming region, the magnesium-lime-silicate glass, and the phosphate glasses showed no surface  $\text{Na}_2\text{O}$ -rich layer on glass films. These glass films with surface  $\text{Na}_2\text{O}$ -rich layer

were supposed to have stronger bonding on Ti substrate.

In chapter 6, the freestanding ultrathin glass films prepared in chapter 5 were bonded on Ti plate by the corrosion-reconstruction bonding method at room temperature. These glass films could also bond on Ti plate by using water as bonding agent at room temperature, however, there bonding strength varied. It has been found that glass films with surface Na<sub>2</sub>O-rich layer had a higher bonding strength on Ti plate. However, this Na<sub>2</sub>O-rich layer was not the necessary condition for high bonding strength, as the phosphate glass and soda-silicate glass films without this layer also had high bonding strength. High solubility in water was investigated to be the condition for strong bonding between glass films and Ti plate based on the experiment results, which was possessed by silicate glasses with low SiO<sub>2</sub> and CaO, high Na<sub>2</sub>O content, and phosphate glasses.

Chapter 7 summarized the corrosion-reconstruction bonding method in this thesis. Based on the freestanding ultrathin glass films and the corrosion-reconstruction bonding, various kind of glass coating on substrate with different functions, such as bioactive coating, optical waveguide, protective coatings, et al, has potential to be constructed with simple process at room temperature.

備考：論文要旨は、和文 2000 字と英文 300 語を 1 部ずつ提出するか、もしくは英文 800 語を 1 部提出してください。

Note : Thesis Summary should be submitted in either a copy of 2000 Japanese Characters and 300 Words (English) or 1 copy of 800 Words (English).

注意：論文要旨は、東工大リサーチリポジトリ(T2R2)にてインターネット公表されますので、公表可能な範囲の内容で作成してください。

Attention: Thesis Summary will be published on Tokyo Tech Research Repository Website (T2R2).