

論文 / 著書情報
Article / Book Information

題目(和文)	Fe 相中の溶質元素の相互拡散によるC14 Laves 相の形成挙動
Title(English)	Formation behavior of C14 Laves phase under the interdiffusion of solute elements in the Fe phase
著者(和文)	LeeDosung
Author(English)	Dosung Lee
出典(和文)	学位:博士(工学), 学位授与機関:東京工業大学, 報告番号:甲第12811号, 授与年月日:2024年6月30日, 学位の種別:課程博士, 審査員:木村 好里,中田 伸生,尾中 晋,小林 郁夫,寺田 芳弘
Citation(English)	Degree:Doctor (Engineering), Conferring organization: Tokyo Institute of Technology, Report number:甲第12811号, Conferred date:2024/6/30, Degree Type:Course doctor, Examiner:,,,,
学位種別(和文)	博士論文
Category(English)	Doctoral Thesis
種別(和文)	論文要旨
Type(English)	Summary

(博士課程)
Doctoral Program

論文要旨

THESIS SUMMARY

系・コース : Department of Graduate major in	材料 材料	系 コース	申請学位 (専攻分野) : Academic Degree Requested	博士 Doctor of	(Engineering)
学生氏名 : Student's Name	Lee Dosung		審査員主査 : Chief Examiner	木村 好里	

要旨 (英文 800 語程度)

Thesis Summary (approx.800 English Words)

Ferritic stainless steels have been received attention for the high temperature application such as automobile exhaust manifolds and interconnect of solid oxide fuel cells. The challenging issue which I am interested in is the high temperature long-term durability regarding mechanical properties and oxidation resistance. In the ferritic stainless steels, Nb and Mo are important alloying elements mainly for the solid solution hardening. At high temperatures, these solute elements induce the precipitation of intermetallic compound (IMC) phase in the α Fe matrix. Our research group has conducted a systematic research project in the Fe-Cr-Nb-Mo quaternary model alloy system to understand microstructure changes according to the IMC precipitates such as C14 Laves phase, χ , μ , and σ phases in the temperature range between 973 and 1173K under the various different heat treatment conditions as well as the oxidation conditions. All microstructure change involves atomic diffusion.

In Chapter 1, General background, motivation, problem assessment, and strategy of the present doctoral thesis research is explained. The two-fold objective of the present doctoral thesis research is stated as well. One is to quantitatively evaluate interdiffusion coefficients in the Fe-Cr-Mo and Fe-Cr-Si ternary systems as the fundamental database using the Boltzmann-Matano based Whittle-Green method. Another is to understand the formation mechanism of C14 Laves phase at the diffusion couple interface of α Fe/Nb and α Fe/Mo under interdiffusion.

In Chapter 2, The both Fe-Cr-Nb and Fe-Cr-Mo ternary systems are the important subsystems, however, the solubility of Nb in α Fe is restricted too low to apply the Boltzmann-Matano based method. Thus, the Fe-Cr-Mo ternary system is centered to determine the interdiffusion coefficients of solute elements in the α Fe. The main interdiffusion coefficients, \bar{D}_{CrCr}^{Fe} , \bar{D}_{MoMo}^{Fe} , and cross interdiffusion coefficients, \bar{D}_{CrMo}^{Fe} , \bar{D}_{MoCr}^{Fe} , in the α Fe phase are determined at 1073K. It is revealed that the diffusivity of Mo is higher than Cr in the α Fe in the Fe-Cr-Mo ternary system and the both cross interdiffusion coefficients have positive signs so that Cr and Mo have accelerating effect with each other on diffusion in the α Fe.

In Chapter 3, since Si affects the precipitation of IMC phase and oxidation as reported in our research group, the Fe-Cr-Si ternary system is subjected to determine the interdiffusion coefficients as well. The main interdiffusion coefficients, \bar{D}_{CrCr}^{Fe} , \bar{D}_{SiSi}^{Fe} , and cross interdiffusion coefficients \bar{D}_{CrSi}^{Fe} , \bar{D}_{SiCr}^{Fe} , in the α Fe phase are determined at 1073K. As a result, it is revealed that the diffusivity of Si is higher than Cr in the α Fe. The value of \bar{D}_{CrCr}^{Fe} in the Fe-Cr-Si ternary system was larger than that in the Fe-Cr-Mo system at 1073 K. The both cross interdiffusion coefficients have negative signs so that Cr and Si have suppressing effect with each other on diffusion in the α Fe.

In Chapter 4, the formation mechanism of C14 Laves phase Fe_2Nb was examined under the interdiffusion at the α Fe/Nb interface was examined by observing and analyzing microstructure, i.e. the process of phase layer formation, starting from non-equilibrium toward equilibrium state. The preformation of metastable phases is required to form the Fe_2Nb under the non-equilibrium condition as to help complete the diffusion path connecting between α Fe and Nb since these elements have a quite low solubility with each other. The preformed metastable phases are η Fe_2Nb_3 , FCC (face centered cubic) Nb, and FCT (face centered tetragonal) Nb. Additionally, the effect of Cr on the formation of C14 Laves phase was examined at the Fe-20Cr(α Fe)/Nb (at.%) diffusion couple interface. It was revealed that Cr has a suppressing effect on the formation of C14 Laves phase compared to the binary α Fe/Nb diffusion couple.

In Chapter 5, the formation mechanism of C14 Laves phase Fe_2Mo was examined under the interdiffusion at the α Fe/Mo interface was examined. The preformation of metastable FCT Mo and stable μ phase Fe_7Mo_6 is required to form the Fe_2Mo . The Fe_2Mo forms at the α Fe/ μ interface. To understand the

competitive effect of Nb and Mo, the formation of C14 Laves phase at the α Fe/50Nb50Mo (at.%) diffusion couple interface was examined. The ternary C14 Laves phase $\text{Fe}_2(\text{Nb},\text{Mo})$ forms at the interface between α Fe and Nb-rich metastable layer. It was revealed that the diffusion of Nb is the controlling factor for the formation of C14 Laves phase.

In Chapter 6, the main results and findings obtained in the present doctoral thesis from chapter 2 through chapter 5 were summarized. The quantitative evaluation of interdiffusion coefficients can be utilized as a database which would have chance to contribute to the theoretical calculation and materials informatics. Understanding of the formation mechanism of C14 Laves phase at the diffusion couple interface not only includes important scientific findings but also enables more accurate precipitation control. Consequently, all these achievements would lead to the establishment of the new material design concept for ferritic stainless steels as the final goal.

備考：論文要旨は、和文 2000 字と英文 300 語を 1 部ずつ提出するか、もしくは英文 800 語を 1 部提出してください。

Note : Thesis Summary should be submitted in either a copy of 2000 Japanese Characters and 300 Words (English) or 1copy of 800 Words (English).

注意：論文要旨は、東工大リサーチリポジトリ(T2R2)にてインターネット公表されますので、公表可能な範囲の内容で作成してください。

Attention: Thesis Summary will be published on Tokyo Tech Research Repository Website (T2R2).