

論文 / 著書情報
Article / Book Information

題目(和文)	電極触媒反応活性に与える白金マイクロ及びメソポーラス構造の影響に関する研究
Title(English)	Study on the effect of platinum micro- and mesoporous structures on the electrocatalytic reaction kinetics
著者(和文)	中原康太
Author(English)	Kota Nakahara
出典(和文)	学位:博士(工学), 学位授与機関:東京科学大学, 報告番号:甲第352号, 授与年月日:2025年3月26日, 学位の種別:課程博士, 審査員:荒井 創,稲木 信介,平山 雅章,山中 一郎,鈴木 耕太
Citation(English)	Degree:Doctor (Engineering), Conferring organization: Institute of Science Tokyo, Report number:甲第352号, Conferred date:2025/3/26, Degree Type:Course doctor, Examiner:,,,,
学位種別(和文)	博士論文
Category(English)	Doctoral Thesis
種別(和文)	論文要旨
Type(English)	Summary

(博士課程)

Doctoral Program

論文要旨

THESIS SUMMARY

系・コース： 応用化学 系
Department of Graduate major in エネルギー コース
学生氏名： 中原 康太
Student's Name

申請学位 (専攻分野)： 博士 (工学)
Academic Degree Requested Doctor of
審査員主査： 荒井 創
Chief Examiner

要旨 (英文 800 語程度)

Thesis Summary (approx.800 English Words)

Electrocatalytic reactions are essential to effectively utilize electrical energy from renewables by converting it into chemical energy and vice versa. Fuel cells employ electrocatalytic reactions and represent themselves as a promising energy conversion device. However, their widespread use is impeded by the high overpotentials of their electrode reactions, such as oxygen reduction and alcohol oxidation reactions. Reducing the overpotentials currently relies on high-cost platinum-based electrocatalysts. Previous studies have attempted to decrease platinum electrocatalyst loading by increasing their surface area and specific activity. In the meantime, little attention has been paid to the specific activity modification of platinum porous electrocatalysts due to the difficulty of the structural control. It would be possible to further reduce the novel metal usage if the specific activity can be enhanced in porous electrocatalysts. Therefore, this study aims to elucidate the effect of platinum micro- and mesopores on the reaction kinetics. The analysis was aided by employing platinum porous electrodes containing one-dimensional pores with regulated diameters of 1.3, 1.8, and 3.0 nm, and varied lengths. The kinetics of the oxygen reduction and alcohol (methanol, ethanol, and ethylene glycol) oxidation reactions are correlated with the structures of the porous and planar electrodes, and the origin of the resultant kinetic change is discussed. This doctoral dissertation comprises the following five chapters.

Chapter 1 is the introduction, including fundamental descriptions of fuel cells and the oxygen reduction and alcohol oxidation reactions. The emphasis is placed on strategies to reduce their reaction overpotentials by modifying the interfacial structure between electrocatalysts and electrolytes. This section also describes the previously reported effect of nanoporous structures on their surface catalytic sites, related electronic structures, and electrolyte states.

Chapter 2 describes experimental procedures, such as fabricating the porous electrodes using surfactant templates coupled with electrodeposition. It also describes the characterization methods for electrocatalytic measurement, structural analysis, and electronic structure analysis of the electrodes. In addition, it includes a numerical simulation method for calculating the oxygen concentration profiles in the nanopores.

Chapter 3 describes the results and discussions for the oxygen reduction activity. Firstly, the effect of the pore length was investigated. A longer pore length increased the apparent current due to its enhanced electrochemical surface area. However, a longer pore increases the mass transport resistance and decreases the utilization ratio of Pt surface atoms. Then, the pore length was reduced to mitigate the mass transport resistance, and the reaction kinetics of the porous electrodes with different pore diameters were evaluated in 0.1 mol dm⁻³ KOH and HClO₄ solutions. The kinetic enhancement for the porous electrodes relative to the planar electrode in the acidic medium is more significant than that in the alkaline medium. This is because the porous electrodes

likely possess concave stepped sites, which show high oxygen reduction kinetics in the acidic medium. Moreover, the oxygen reduction kinetics follow a volcano relationship with a kinetic maximum at a pore diameter of 1.8 nm in both solutions. The catalytic trend is ascribed to the d-band center downshift caused by the compressive strain with a decrease in the pore size. Furthermore, the effect of alkali metal cations on the oxygen reduction kinetics was investigated in 0.1 mol dm⁻³ MOH (M = Li, Na, K, Cs) solutions. While the oxygen reduction kinetics show volcano relationships in the K⁺- and Cs⁺-containing solutions, clear kinetic trends are not observed in Na⁺- and Li⁺-containing solutions due to the strong modification of adsorption energy by the hydrate cations at the catalytic interface.

Chapter 4 describes the results and discussions for the alcohol oxidation activity in 1 mol dm⁻³ alcohol-containing 1 mol dm⁻³ KOH. The apparent reaction currents increased for the porous electrodes in comparison to the planar electrode due to their enhanced electrochemical surface area. In methanol oxidation reactions, the reaction kinetics decreased with a decrease in the pore size. This is consistent with the d-band center downshift, which is unfavorable for the dehydrogenation reaction. The porous electrodes exhibited more tolerance toward surface poisoning due to the faster oxidation kinetics of carbon monoxide. In ethanol and ethylene glycol oxidation reactions, the kinetics and stabilities were enhanced with the porous model electrodes compared to the planar surface. However, the kinetics decreased when the pore size was too small. These origins were correlated with the change in the adsorption energy of the reaction species caused by the nanoporous structure.

Chapter 5 describes the conclusions and outlook. The above results show that the porous electrodes with specific pore sizes enhance the kinetics of the oxygen reduction and alcohol oxidation reactions. The increase in the stability against poisoning was also observed for the latter. These findings emphasize the importance of tuning the electrocatalyst porous structure not only to obtain high surface area but also to enhance the electrocatalytic activity and stability. Furthermore, since the electronic structure dictates the kinetics of other electrocatalytic reactions, such as oxygen evolution, hydrogen evolution/oxidation, CO₂ reduction, and nitrogen reduction reactions, tuning pore structure is a promising approach for improving the kinetics of various electrocatalytic reactions.

備考：論文要旨は、和文 2000 字と英文 300 語を 1 部ずつ提出するか、もしくは英文 800 語を 1 部提出してください。

Note : Thesis Summary should be submitted in either a copy of 2000 Japanese Characters and 300 Words (English) or 1 copy of 800 Words (English).

注意：論文要旨は、東京科学大学リサーチリポジトリ (T2R2) にてインターネット公表されますので、公表可能な範囲の内容で作成してください。

Attention: Thesis Summary will be published on Science Tokyo Research Repository Website (T2R2).