

論文 / 著書情報
Article / Book Information

| | |
|-------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| 題目(和文) | |
| Title(English) | Formation and Applications of SiC Nanowires Synthesized by Thermal Evaporation Method |
| 著者(和文) | JiraborvornpongsaNoppasint |
| Author(English) | Noppasint Jiraborvornpongsa |
| 出典(和文) | 学位:博士(工学), 学位授与機関:東京工業大学, 報告番号:甲第9749号, 授与年月日:2015年3月26日, 学位の種別:課程博士, 審査員:矢野 豊彦,若井 史博,篠崎 和夫,中島 章,安田 公一 |
| Citation(English) | Degree:, Conferring organization: Tokyo Institute of Technology, Report number:甲第9749号, Conferred date:2015/3/26, Degree Type:Course doctor, Examiner:,,,, |
| 学位種別(和文) | 博士論文 |
| Category(English) | Doctoral Thesis |
| 種別(和文) | 論文要旨 |
| Type(English) | Summary |

論文要旨

THESIS SUMMARY

専攻 : Metallurgy and Ceramics Science 専攻
Department of

学生氏名 : JIRABORVORNPNONGSA Noppasint
Student's Name

申請学位 (専攻分野) : 博士 (Engineering)
Academic Degree Requested Doctor of

指導教員 (主) : Prof. YANO Toyohiko
Academic Advisor(main)

指導教員 (副) :
Academic Advisor(sub)

要旨 (英文 800 語程度)

Thesis Summary (approx.800 English Words)

Chapter 1 “Introduction” Background and objective of this research are mentioned in this chapter. It is well-known that SiC nanowires have excellent properties, such as high mechanical strength, high thermal conductivity and high thermal stability, thus SiCNWs are attractive materials for application in nano-electronic devices and reinforcement of composite materials. Thermal evaporation method is an effective and un-complex way to synthesize relatively high yield of SiCNWs without addition of catalyst. However, the formation mechanism of SiCNWs synthesized by thermal evaporation method is still unclear and the applications of SiCNWs is still limited. Therefore, research on the growth mechanism of SiCNWs, including study on their applications are meaningful. The objectives of this research are as follows; (1) Confirm synthesis process of SiCNWs and clarify the formation mechanism, (2) Clarify the effects of SiCNWs addition on the properties of alumina ceramics, (3) Clarify the effects of magnetic field on the alignment of SiCNWs in alumina matrix composite.

Chapter 2 “Synthesis, Characterization and Formation Mechanism of SiC Nanowires” A simple thermal evaporation of silicon powders during decomposition of CH₄ in a mullite tube furnace was used to synthesize SiCNWs. Large amount of long SiCNWs with smooth-surface were obtained and their average diameters were 45 nm and up to 1 μm long. These nanowires had a single crystal β-SiC core and amorphous SiO₂ shell. During the formation of SiCNWs in this process, exhaust gases were analyzed by gas chromatography and the growth activity of SiCNWs was captured by the digital camera. CO gas was detected from the exhaust gases of the production system only when SiCNWs were quickly growing. From these experimental results, it was confirmed that CO gas was one of the main byproduct of the SiCNWs formation. The formation reaction of SiCNWs should be:



The SiCNWs formation was discussed by oxide-assisted-growth mechanism. Moreover, the oxygen content in the starting silicon powder was also important, it had to be about 20 wt% to obtain highest amount of SiC nanowires in this synthesis process.

Chapter 3 “Effects of β-SiC/SiO₂ Core-Shell Nanowires as an Adding Material on the Properties of Alumina Matrix Composite” Alumina matrix composites reinforced with very small amount of SiCNWs prepared by hot-pressing was characterized. Alumina matrix specimens that contained SiC nanopowder were prepared for comparison. Grain sizes of SiC-added alumina specimens were one fifth of that of the monolithic one. Vickers hardness of both SiC nanowires and SiC nanopowder-added specimens were higher than monolithic alumina around 10%. Fracture toughness decreased ~15% both in SiC nanowires and SiC nanopowder-contained specimens. Thermal conductivity of specimens was increased with increasing the amount of SiCNWs. It was found out that the SiCNW is a better additive for increasing thermal conductivity of the alumina matrix composites, than the SiC nanopowder due to its wire shape. As a result, adding 0.2 wt% of the SiCNWs increased the thermal conductivity of alumina by as much as 45%. From these results, it was clarified that only small amount of nano-sized SiC as an additive material has a large effect on properties of alumina matrix composite.

Chapter 4 “Effects of Strong Magnetic Field on the Alignment of SiC Nanowires in Alumina Matrix Composites” SiCNWs were successfully dispersed in water by ultrasonic homogenizer and the zeta potential of SiCNWs in water were analyzed. Dense alumina matrix composites containing 1 wt% SiCNWs were prepared by colloidal processing, consolidated by slip-casting in a strong magnetic field (12 T) and sintered by SPS or milliwave sintering. In general, it is difficult to control the orientation of the material with cubic crystal structure by a magnetic field under normal circumstance. However, it was found that the alignment of SiCNWs was mainly dominated by the direction of magnetic field. SiCNWs were aligned parallel to the direction of magnetic field due to the anisotropic of magnetic susceptibility cause by the stacking faults. And some of SiCNWs were aligned perpendicular to the slip-casting direction due to the capillary force and pressure during sintering. Sinterability of the alumina matrix composite containing SiCNWs was improved by aligned SiCNWs in horizontal direction to the pressing direction. The Vickers hardness and elastic modulus of the slip-casted specimen in the horizontal direction were higher than those of the specimen slip-casted without the magnetic field. Furthermore, milliwave sintering method was an effective method to densify alumina matrix composites containing SiCNWs at lower temperature than SPS.

Chapter 5 “Summary” Finally, this chapter summarized the important results and findings in this thesis.

備考：論文要旨は、和文 2000 字と英文 300 語を 1 部ずつ提出するか、もしくは英文 800 語を 1 部提出してください。

Note : Thesis Summary should be submitted in either a copy of 2000 Japanese Characters and 300 Words (English) or 1copy of 800 Words (English).

注意：論文要旨は、東工大リサーチリポジトリ(T2R2)にてインターネット公表されますので、公表可能な範囲の内容で作成してください。

Attention: Thesis Summary will be published on Tokyo Tech Research Repository Website (T2R2).