

論文 / 著書情報
Article / Book Information

題目(和文)	原子ステップサファイアc面基板由来のNiO系回折格子ナノ構造に関する研究
Title(English)	Study on NiO-Based Grating Nanostructure Derived from Atomically Stepped Sapphire (0001) Substrate
著者(和文)	山内涼輔
Author(English)	Ryosuke Yamauchi
出典(和文)	学位:博士(工学), 学位授与機関:東京工業大学, 報告番号:甲第9826号, 授与年月日:2015年3月26日, 学位の種別:課程博士, 審査員:吉本 護,北本 仁孝,舟窪 浩,彌田 智一,三宮 工
Citation(English)	Degree:, Conferring organization: Tokyo Institute of Technology, Report number:甲第9826号, Conferred date:2015/3/26, Degree Type:Course doctor, Examiner:,,,,
学位種別(和文)	博士論文
Category(English)	Doctoral Thesis
種別(和文)	要約
Type(English)	Outline

(博士課程)
Doctoral Program

論文要約

専攻：	物質科学創造	専攻
Department of		
学生氏名：	山内 涼輔	
Student's Name		

申請学位 (専攻分野)：	博士	(工学)
Academic Degree Requested	Doctor of	
指導教員 (主)：	吉本 護	
Academic Advisor(main)		
指導教員 (副)：	北本 仁孝	
Academic Advisor(sub)		

NiO has multifunctional properties, and can be used for UV detectors, electrochromic devices, organic solar cells, and UV-light emitting diodes as examples. Effectively controlling the size, morphology, and structure of NiO nanomaterials is imperative for applications involving the morphology-dependent properties. Hence, the development of NiO nanostructured materials is stimulating worldwide interests. According to previous works in my laboratory, periodic straight nanogroove arrays were formed on room-temperature pulsed laser deposited NiO(111) epitaxial thin films grown on atomically stepped sapphire (0001) substrates by annealing in air. To my knowledge, there are no other self-organizing formation methods of NiO periodic straight nanostructures that have potential applications for UV plasmonics and UV photonics, but the formation mechanism was unknown. Understanding the formation mechanism could conduce to the nanogroove size control for the industrial applications. Therefore, the influence of various conditions on the NiO periodic straight nanogroove array formation derived from the atomically stepped sapphire (0001) substrate was investigated. Firstly, the nanogroove array was formed via rapid thermal annealing (RTA) to optimize the formation time and to effectively fabricate the sample. The array formation took approximately 60 s at 973 K. The nanogroove formation process time reduced to 1/100 of the previous research. Secondly, the influence of the sapphire substrate terrace width on the array formation was investigated. The nanogroove periodicity corresponded well with the used substrate terrace width of the 0.22-nm-high stepped sapphire (0001) substrate. It was of great interest that the two types of 180°-rotated triangular crystalline domain were alternately grown on each film terrace divided by the nanogrooves. In addition, the two types of triangle crystals were not mixed on one film terrace. The origin of the morphology was important to understand the formation mechanism.