

論文 / 著書情報  
Article / Book Information

|                   |  |
|-------------------|--|
| 題目(和文)            | 窒素原子含有骨格を用いた新規棒状液晶材料の研究：合成、液晶性の評価、自己組織化と電気特性   |
| Title(English)    | Novel Calamitic Liquid Crystals Based on N-containing Mesogens: Synthesis, Characterization of Liquid Crystallinity, Self-organization and Electrical Properties             |
| 著者(和文)            | YangTengzhou   |
| Author(English)   | Tengzhou Yang  |
| 出典(和文)            | 学位:博士(工学),<br>学位授与機関:東京工業大学,<br>報告番号:甲第10343号,<br>授与年月日:2016年9月20日,<br>学位の種別:課程博士,<br>審査員:飯野 裕明,加藤 隆志,梶川 浩太郎,大見 俊一郎,穴戸 厚,石川 謙  |
| Citation(English) | Degree:.,<br>Conferring organization: Tokyo Institute of Technology,<br>Report number:甲第10343号,<br>Conferred date:2016/9/20,<br>Degree Type:Course doctor,<br>Examiner:,,,,, |
| 学位種別(和文)          | 博士論文   |
| Category(English) | Doctoral Thesis  |
| 種別(和文)            | 論文要旨   |
| Type(English)     | Summary  |

(博士課程)  
Doctoral Program

## 論文要旨

THESIS SUMMARY

|                          |               |  |              |
|--------------------------|---------------|--|--------------|
| 専攻 :<br>Department of    | 物理電子システム創造 専攻 | 申請学位 (専攻分野) :<br>Academic Degree Requested | 博士 (工学)      |
| 学生氏名 :<br>Student's Name | Yang Tengzhou | 指導教員 (主) :<br>Academic Advisor(main)       | Hiroaki Iino |
|                          |               | 指導教員 (副) :<br>Academic Advisor(sub)        | Takashi Kato |

要旨 (英文 800 語程度)

Thesis Summary (approx.800 English Words)

In this research, we proposed a new study to utilize a liquid crystalline molecule as a material platform so as to induce new and/or enhanced properties by designing N-containing moieties as mesogenic skeleton. Three kinds of liquid crystalline semiconductors based on functional N-containing heteroaromatic skeletons were prepared through facile synthetic routes, namely, benzo[c]cinnoline (BC), monoimide-substituted, and isoquino[8,7-h]isoquinoline (IQIQ) derivatives.

In the chapter 1, firstly, the research progress on organic semiconductors and liquid crystalline semiconductors has been reviewed, and also the research background was discussed. Taking account of the unique properties of liquid crystals, it is worth expecting that liquid crystals could be a material platform for developing new properties when various functional units are incorporated into their characteristic molecular systems. In addition, N-containing moieties are important functional units for optic and electronic materials. The incorporation of N-containing moieties into the central mesogenic skeleton can effectively induce large  $\pi$ -polarization thereby giving rise to the directed molecular dipole or strong electron affinity. Hence, in my research, some liquid crystalline semiconductors based on N-containing heteroaromatic skeletons as main functional units have been prepared.

In the chapter 2, experimental methods are described in detail. We tried to prepare every compounds using short synthetic route to avoid the contamination of chemical impurities. After obtaining the relative compounds, their molecular structures were confirmed by <sup>1</sup>HNMR and MS spectrum. And then the phase transition could be measured by using DSC and POM, in which molecular orientation was checked by X-ray diffraction. Finally, high-purity samples can be used to transient photocurrent measurements by time-of-flight (TOF) technique, and thus the charge carrier mobility can be evaluated.

In the chapter 3, a series of liquid crystals based on polar BC framework were prepared through facile and versatile synthetic strategies. Dialkylated BC derivatives of 10-Ph-BC-Ph-10 and 12-Ph-BC-8 showed Smectic(Sm)C phase over a wide temperature range (>150°C) and highly ordered SmG(or SmJ) and SmH(or SmK) phases, while monoalkylated derivatives of Ph-BC-8 and BC-Ph-8 showed only low-ordered mesophases of Nematic and SmA phases. The pronounced reversible redox waves and low-lying LUMO levels of these derivatives approximately -3.2eV estimated by CVs revealed their potential n-type charge transport nature. In addition, temperature-dependent transport behaviors revealed by TOF method in SmA and SmC phases make us acquire a good knowledge of that dipole moment existed in polar mesogens will enhance the energetic disorder resulting in a temperature-dependent mobility. Furthermore, the wide temperature range of the SmC phase in dialkylated BC derivatives in addition with their large dipole moments (> 3.4 Debye) perpendicular to the long molecular axis made them become promising candidates for ferroelectric liquid crystals. A clear switching behavior in POM textures was observed, which was originated from ferroelectricity induced in the SmC\* by a small amount chiral dopant.

In the chapter 4, a series of novel liquid crystals based on monoimide-fused aromatic skeleton, with large dipole along the long molecular axis, were prepared with moderate yields. Low ordered SmA phase in a head-to-tail arrangement within the layers was achieved for NAPI-Tp(2)-8, while highly ordered smectic mesophases for DiCN-NAPI-Ph-12 and ANTI-Ph-12. Temperature-dependent unipolar electron transport behavior in the SmA phase of NAPI-Tp(2)-8 by TOF technique was revealed with mobility on the order of 10<sup>-5</sup>cm<sup>2</sup>/Vs at a limited temperature range of 20K, which was resulted from the big dipole moment randomly distributed mesogenic molecules within the SmA phase. Highly ordered smectic mesophases and low LUMO levels below -3.6eV were realized in DiCN-NAPI-Ph-12 and ANTI-Ph-12 revealed that they are potential materials for n-channel FET.

In the chapter 5, a series of new calamitic liquid crystals based on aza-fused IQIQ skeleton were successfully synthesized through facile and versatile synthetic route in a moderate yield. 10-IQIQ-10

only exhibited low ordered smectic mesophase, while didodecyl-substituted 12-IQIQ-12 and ditetradecyl-substituted 14-IQIQ-14 exhibited highly ordered smectic mesophases. In addition, the dicaynated compound DiCN-Chrysene-12 also presented the emergence of highly ordered smectic mesophase. Charge carrier transport property of 12-IQIQ-12 was characterized by TOF technique, revealing that electron and hole mobilities are on the order of  $10^{-4}$  cm<sup>2</sup>/Vs, which depends neither temperature nor electric field. Low LUMO level of -3.33eV for 12-IQIQ-12 and -3.72eV for DiCN-Chrysene-12, suggesting that they are potential electron-transporting candidates. Highly ordered smectic mesophases combined with low LUMO levels in these derivatives revealed that they were promising candidates for n-channel FET.

Through this study on the synthesis, liquid crystallinity and electric properties of liquid crystals based on N-containing heteroaromatic skeletons, the expected properties were realized such as the controlled directed molecular dipole and strong electron affinity. The conclusion is generally summarized: 1. Induced ferroelectricity has been realized in liquid crystalline benzocinnoline derivative with broad SmC phase; 2. The dipole moment along the molecular long axis in the rod-shaped mesogens can facilitate and stabilize the formation of smectic mesophases; 3. Highly ordered smectic mesophases combined with low LUMO levels were realized demonstrating their potential applications in n-channel FETs. Generally, the synthesized calamitic liquid crystals based on N-containing mesogens in this thesis become promising candidates in ferroelectric liquid crystals and n-channel FETs.

備考：論文要旨は、和文 2000 字と英文 300 語を 1 部ずつ提出するか、もしくは英文 800 語を 1 部提出してください。

Note : Thesis Summary should be submitted in either a copy of 2000 Japanese Characters and 300 Words (English) or 1 copy of 800 Words (English).

注意：論文要旨は、東工大リサーチリポジトリ(T2R2)にてインターネット公表されますので、公表可能な範囲の内容で作成してください。

Attention: Thesis Summary will be published on Tokyo Tech Research Repository Website (T2R2).