

論文 / 著書情報  
Article / Book Information

|                   |  |
|-------------------|--|
| 題目(和文)            |  |
| Title(English)    | Structure and Properties of Biodegradable Fibers of PHBH Produced by High-Speed Melt Spinning Process  |
| 著者(和文)            | 秦青   |
| Author(English)   | Qing Qin   |
| 出典(和文)            | 学位:博士(工学),<br>学位授与機関:東京工業大学,<br>報告番号:甲第10445号,<br>授与年月日:2017年3月26日,<br>学位の種別:課程博士,<br>審査員:鞠谷 雄士,扇澤 敏明,塩谷 正俊,浅井 茂雄,松本 英俊  |
| Citation(English) | Degree:Doctor (Engineering),<br>Conferring organization: Tokyo Institute of Technology,<br>Report number:甲第10445号,<br>Conferred date:2017/3/26,<br>Degree Type:Course doctor,<br>Examiner:,,,, |
| 学位種別(和文)          | 博士論文   |
| Category(English) | Doctoral Thesis  |
| 種別(和文)            | 論文要旨   |
| Type(English)     | Summary  |

(博士課程)  
Doctoral Program

## 論文要旨

THESIS SUMMARY

専攻： 有機・高分子物質 専攻  
Department of  
学生氏名： 秦 青  
Student's Name

申請学位(専攻分野)： 博士 (工学)  
Academic Degree Requested Doctor of  
指導教員(主)： 鞠谷 雄士  
Academic Advisor(main)  
指導教員(副)：  
Academic Advisor(sub)

要旨(英文 800 語程度) Thesis Summary (approx. 800 English Words)

Poly(3-hydroxybutyrate-co-3-hydroxyhexanoate) (PHBH) is one of the PHB based co-polymers known as a melt-processable aliphatic co-polyester. Melt processing of this polymer is not easy because the glass transition temperature of PHBH is below the room temperature whereas the crystallization rate of this polymer is extremely low. Accordingly, it is difficult to form fibers, films and other products from PHBH because the polymer can be still in a rubbery state after it cools down to the room temperature in the melt processing. In this research, attempts were made to overcome the low crystallizability of PHBH in the melt processing by applying the high-speed melt spinning process.

In chapter 2, PHBHs with high and low 3HH compositions of 10.4 mol% (PHBH-H) and 5.4 mol% (PHBH-L) were subjected to the high-speed melt spinning process. Considering that the PHBHs are susceptible to the thermal degradation, wide range of extrusion conditions were adopted, and the spinning behavior as well as the structure and properties of the resultant as-spun fibers were investigated. For the PHBH-H fibers, low oriented  $\alpha$ -form crystals were formed at high take-up velocities, however sticking among fibers could not be avoided because of the low crystallizability of the polymer. On the other hand, enhancement of crystallization at high take-up velocities was confirmed in the high-speed melt spinning of PHBH-L fibers. Thermal decomposition caused significant effects on spinning and structure development behaviors. Accordingly, fiber structure development was promoted under the extrusion conditions of low extrusion temperature and high through-put rate. Applying the high-speed melt spinning process, separated fibers were obtained even at high extrusion temperature of 180 °C, the temperature higher than the melting temperature of pure PHB where crystalline nucleus of PHB is known to disappear. Wide-angle X-ray diffraction (WAXD) analysis of the as-spun fibers showed that the crystalline orientation of  $\alpha$ -form crystals increased with an increase in the take-up velocity. A small amount of  $\beta$ -form crystals started to appear at high take-up velocities. This was another evidence for the occurrence of crystallization under high tensile stress in the spin-line. Lowering of the melting peak temperature observed in the DSC analysis of as-spun fibers of high take-up velocities also corresponded to the starting of orientation-induced crystallization in the spin-line.

In chapter 3, detailed analysis on the structure of high-speed spun PHBH fibers was carried out paying a particular attention to the formation of  $\beta$ -form crystals. Enhancement of crystallization at high take-up velocities was confirmed in the high-speed melt spinning of PHBH-L fibers, and the crystalline orientation of the  $\alpha$ -form crystals increased with increasing take-up velocity. On the other hand, development of  $\beta$ -form crystals was noted from the reflection on the equator in the WAXD patterns of the fibers prepared at high take-up velocities. The fraction of  $\beta$ -form crystals increased under the spinning conditions with higher spin-line stress. PHBH fibers showed negative birefringence because of the negative intrinsic birefringence of the  $\alpha$ -form crystal. With the increase of take-up velocity, absolute value of birefringence increased and then started to decrease from the take-up velocity where the  $\beta$ -form crystals started to appear. This was considered to be due to the positive intrinsic birefringence of the  $\beta$ -form crystal. During the in-situ measurement of WAXD patterns in the heating process of as-spun fibers, melting of the  $\beta$ -form crystals was observed in the temperature range from 90 to 130 °C, which is lower than the melting temperature of the  $\alpha$ -form crystal. Mechanical properties of as-spun fibers increased with an increase in the take-up velocity. The highest tensile strength and tensile modulus of 156 MPa and 2.43 GPa were obtained under the conditions of take-up velocity 6 km/min, extrusion temperature 180 °C and total through-put rate for four filaments 10 g/min. The tensile strength of the as-spun fibers showed positive correlation with the  $\beta$ -form fraction.

In chapter 4, with the aim of investigating the effect of thermal decomposition in the extrusion process in detail, low 3HH composition PHBHs of four different melt flow indices (MI) were subjected to the high-speed melt spinning process. Temperature dependence of rate constant for the thermal decomposition showed similar tendency for polymers of different MIs. On the other hand, condition for obtaining separated fibers shifted to higher take-up velocities with increasing MI. It is worth noting that the effect of throughput rate on the structure development behavior showed opposite tendency for the polymers of high and low MIs. With the decrease of throughput rate, structure development of the low MI polymer was suppressed whereas that of the high MI polymer was enhanced. It was considered that the effect of enhanced viscosity reduction dominated the structure formation behavior in the former case, whereas the effect of the increase of draw-down ratio in the spinning process dominated the structure formation behavior in the latter case.

In chapter 5, high-speed melt spinning of sheath-core bicomponent fibers was carried out using the PHBH-L and PHBH-H as the sheath and core components, respectively. Molecular orientation of the sheath component of PHBH-L was high while that of the core component of PHBH-H was extremely low even at high take-up velocities especially when extrusion temperature was high. This was considered to be due to the orientation relaxation of PHBH-H component in the spin-line after the orientation-induced crystallization and subsequent solidification of PHBH-L. In comparison with the single component spinning of PHBH-H, advantages of applying the bicomponent spinning with PHBH-L were confirmed to be the collecting of well separated fibers at high take-up velocities as well as the increasing of the attainable highest take-up velocity.

備考：論文要旨は、和文 2000 字と英文 300 語を 1 部ずつ提出するか、もしくは英文 800 語を 1 部提出してください。

Note: Thesis Summary should be submitted in either a copy of 2000 Japanese Characters and 300 Words (English) or 1 copy of 800 Words (English).

注意：論文要旨は、東工大リサーチリポジトリ(T2R2)にてインターネット公表されますので、公表可能な範囲の内容で作成してください。

Attention: Thesis Summary will be published on Tokyo Tech Research Repository Website (T2R2).