

論文 / 著書情報
Article / Book Information

題目(和文)	
Title(English)	Study on the control of distribution of Al atoms in the framework of the MFI-type zeolite
著者(和文)	ビリゲト
Author(English)	Turgen Biligetu
出典(和文)	学位:博士(工学), 学位授与機関:東京工業大学, 報告番号:甲第10654号, 授与年月日:2017年9月20日, 学位の種別:課程博士, 審査員:野村 淳子,馬場 俊秀,鎌田 慶吾,北村 房男,本倉 健
Citation(English)	Degree:Doctor (Engineering), Conferring organization: Tokyo Institute of Technology, Report number:甲第10654号, Conferred date:2017/9/20, Degree Type:Course doctor, Examiner:,,,,
学位種別(和文)	博士論文
Category(English)	Doctoral Thesis
種別(和文)	論文要旨
Type(English)	Summary

論文要旨

THESIS SUMMARY

専攻 : Department of	総合理工学物質電子化学	専攻	申請学位 (専攻分野) : Academic Degree Requested	博士 (工学)	Doctor of
学生氏名 : Student's Name	ビリゲト		指導教員 (主) : Academic Advisor(main)	野村 淳子	
			指導教員 (副) : Academic Advisor(sub)		

要旨 (和文 2000 字程度)

Thesis Summary (approx.2000 Japanese Characters)

The aim of this study is to control the distribution of Al atoms in ZSM-5 zeolite frameworks and to investigate the Al atoms distribution on the catalytic performance. This thesis is composed of six chapters. Chapter I is a comprehensive review focusing on the introduction of zeolites. Chapters II and III focused on the synthesis of ZSM-5 zeolites by using various kinds of organic molecules as OSDA and/or pore-filling agents. Chapter IV focuses on the effect of Al atoms distribution in ZSM-5 on the catalytic performance. Chapter V focuses on the control of crystal size of ZSM-5 with unique Al atoms distribution. Chapter VI is a general conclusion summarizing the significance of the research done in this dissertation.

In Chapter I, there was a comprehensive review on the introduction of zeolites, which included the synthesis, characterizations and catalytic applications of zeolite catalysts, especially the MFI-type (ZSM-5) zeolite. Recent development of the control of Al atoms distribution in zeolite framework was also included.

In Chapter II, ZSM-5 zeolites with different Al distributions were synthesized by using various kinds of organic molecules as structure-directing agents (OSDAs). The obtained samples were characterized by scanning electron microscopy (SEM), X-ray diffraction (XRD), N₂ adsorption-desorption, NH₃-TPD and elemental analysis. The Al atoms distribution in the ZSM-5 zeolites was estimated by constrain index (CI).

In Chapter III, ZSM-5 zeolites with different Al distributions were synthesized by using various kinds of alcohols as pore-filling agents in the presence of Na cations. The obtained samples were characterized by SEM, XRD, NH₃-TPD, and elemental analysis. The Al atoms distribution in the ZSM-5 zeolites was estimated by constrain index (CI).

In Chapter IV, a new class of ZSM-5 zeolites with Al atoms preferentially located at straight and sinusoidal channels were synthesized. It was achieved by using bulky alcohols, such as Trimethylolthane (TME), as pore-filling agents, in combination with Na cation. In this case, considering the size of TME molecule, it would occupy the channel intersections and Na⁺ species are located at straight and sinusoidal channels. Meanwhile, TME molecule has no charge unlike TPA cation so that Al³⁺ species are located near Na⁺ species, resulting in the unique distribution of Al atoms in the MFI framework; Al atoms are preferentially located at straight and sinusoidal channels, not the channel intersections. Thus prepared Al-site controlled ZSM-5 exhibited a longer catalytic life in the cracking of n-hexane and the methanol to olefins (MTO) reaction than that with Al atoms located at the intersections. The part of this work has been published in Journal of Catalysis.

In Chapter V, the crystal size of ZSM-5 zeolites with a unique Al atoms distribution (described in Chapter 4) was controlled. It was achieved by changing the crystal size, type (i.e., as-made, Na-type, NH₃-type, and H-type), and amount of the seeds in the synthesis gel. The produced samples were characterized and applied as catalysts for the MTO reaction. The part of this work is now in preparation for submission.

In Chapter VI, a general summary and future prospect of this study are presented.

備考: 論文要旨は、和文 2000 字と英文 300 語を 1 部ずつ提出するか、もしくは英文 800 語を 1 部提出してください。Note: Thesis Summary should be submitted in either a copy of 2000 Japanese Characters and 300 Words (English) or 1 copy of 800 Words (English).

注意: 論文要旨は、東工大リサーチリポジトリ(T2R2)にてインターネット公表されますので、公表可能な範囲の内容で作成してください。

Attention: Thesis Summary will be published on Tokyo Tech Research Repository Website (T2R2).