

論文 / 著書情報
Article / Book Information

| | |
|-------------------|--|
| 題目(和文) | 高難度選択酸化反応用Fe含有ゼオライト触媒に関する研究 |
| Title(English) | Study on Fe-containing zeolite catalysts for extremely difficult selective oxidation reactions |
| 著者(和文) | XiaoPeipei |
| Author(English) | PEIPEI XIAO |
| 出典(和文) | 学位:博士(工学), 学位授与機関:東京工業大学, 報告番号:甲第10979号, 授与年月日:2018年9月20日, 学位の種別:課程博士, 審査員:野村 淳子,鎌田 慶吾,本倉 健,庄子 良晃,横井 俊之 |
| Citation(English) | Degree:Doctor (Engineering), Conferring organization: Tokyo Institute of Technology, Report number:甲第10979号, Conferred date:2018/9/20, Degree Type:Course doctor, Examiner:,,,, |
| 学位種別(和文) | 博士論文 |
| Category(English) | Doctoral Thesis |
| 種別(和文) | 論文要旨 |
| Type(English) | Summary |

論文要旨

THESIS SUMMARY

| | | | | | |
|--|---------------------------------------|----------|--|-----------------|---------------|
| 系・コース : Department of Electronic Department of Graduate major in | Department of Electronic Chemistry | 系 コース | 申請学位 (専攻分野) : Academic Degree Requested | 博士 Doctor of | (Engineering) |
| 学生氏名 : Student's Name | Xiao Peipei | | 指導教員 (主) : Academic Supervisor(main) | Junko Nomura | |
| | | | 指導教員 (副) : Academic Supervisor(sub) | | |

要旨 (英文 800 語程度)

Thesis Summary (approx.800 English Words)

This thesis is entitled “Study on Fe-containing zeolite catalysts for extremely difficult selective oxidation reactions” and the approaches to obtain highly active Fe-containing zeolites catalysts for extremely difficult selective oxidation reactions, including direct conversion of methane to methanol (MTM) and benzene to phenol (BTP) with H_2O_2 are addressed.

In Chapter 1, which was named the “Introduction”, the research background was described to demonstrate the importance of the thesis.

Chapter 2 entitled “Direct synthesis of phenol by hydroxylation of benzene with hydrogen peroxide over Fe-containing MFI zeolite catalysts” explored the role of different Fe species on Fe-containing MFI zeolites by different methods. Directly synthesized Fe-silicalite-1 achieved better catalytic performance than the post synthesis ones in BTP reaction. The formation of isolated and oligomeric extra framework Fe species played a key role for achieving high yield of phenol. Moreover, post-alkaline treatment was advantageous to the formation of mesopores and oligomeric Fe species on the extra framework, thus the highest phenol yield of 7.6% was achieved.

Chapter 3 entitled “Dramatic impacts of the distribution of Fe species in Fe-silicalite-1 zeolites and solvent on liquid-phase methane conversion to methanol with H_2O_2 ” investigated Fe distribution in Fe-silicalite-1 zeolites using TPAOH as OSDA with or without Na cations. Fe-silicalite-1 zeolites synthesized without Na cations showed more uniform Fe distribution than those synthesized with Na cations. Sulfolane was useful to improve the production of methanol and its stability during MTM reaction. The use of sulfolane in water with an appropriate proportion led to an extremely high methanol production with a high selectivity. Fe-silicalite-1 zeolites synthesized using TPAOH as OSDA without Na cations showed better catalytic performance than those with Na cations possibly due to the position of Fe species.

Chapter 4 entitled “The influence of iron and aluminum location in MFI zeolites on the catalytic performance in hydroxylation of benzene to phenol and methane to methanol with H_2O_2 ” discussed Fe distribution in Fe-ZSM-5 zeolites using TPAOH as OSDA with and without Na cations. Fe-ZSM-5 zeolites synthesized without Na cations ($\text{FZ}(\text{T})_x$) displayed more uniform Fe distribution than those synthesized with Na cations ($\text{FZ}(\text{TN})_y$). In general, $\text{FZ}(\text{T})_x$ zeolites showed better catalytic performance than $\text{FZ}(\text{TN})_y$ in both BTP and MTM reactions. The introduction of Al in $\text{FZ}(\text{T})_x$ zeolites improved the catalytic performance in BTP and MTM reactions, but in $\text{FZ}(\text{TN})_y$ zeolites, the catalytic performance was not obviously increased possibly due to the location of iron and aluminum.

In Chapter 5 entitled “Alkaline treatment on as-synthesized and calcined Fe-silicalite-1 and Fe-ZSM-5 zeolites for hydroxylation of benzene to phenol with H_2O_2 ” the influence of desilication on Fe-ZSM-5 and Fe-silicalite-1 zeolites was researched. Both template and aluminum can prevent desilication and protect the crystal structure. Alkaline treatment was an effective post modification method to affect both the porosity of the zeolite and the nature of Fe species. The increased porosity improved the transport properties, reduced diffusion resistance and increased the active Fe species.

In Chapter 6 entitled “Direct synthesis of Fe-containing MWW zeolite for direct hydroxylation of benzene to phenol and methane to methanol with H_2O_2 ” the effects of calcination temperature on the catalytic performance of Fe-MWW and Fe, Al-MWW were discovered. High temperature calcination to remove OSDA was beneficial to produce more isolated and oligomeric Fe species on the extra framework for Fe-MWW, thus activate the catalytic performance. But the presence of Al in Fe, Al-MWW dispersed Fe and high temperature calcination produced the FeAlO_x species, which may be not beneficial to the catalytic performance. In addition, increasing the calcination temperature to prepare H-type zeolite made more seriously Fe aggregation for both Fe-MWW and Fe, Al-MWW, thus decrease the catalytic performance.

Chapter 7 entitled “Iron- and copper-exchanged Beta zeolite catalysts for hydroxylation of benzene to phenol and methane to methanol with H_2O_2 ” included Fe and/ or Cu exchanged Beta catalysts with varied metal contents. Fe-Cu/Beta catalysts showed dramatically high catalytic activity due to the synergetic effect. 6Fe-6Cu/Beta achieved the highest phenol yield of 10.5 % in BTP reaction and MeOH yield of 720 μmol in MTM reaction. The catalytic stability in the BTP reaction was investigated. The synergetic effect was influenced by the metallic states instead of the content.

Chapter 8 entitled “Summary” gave a summary based on the whole thesis.

備考 : 論文要旨は、和文 2000 字と英文 300 語を 1 部ずつ提出するか、もしくは英文 800 語を 1 部提出してください。

Note : Thesis Summary should be submitted in either a copy of 2000 Japanese Characters and 300 Words (English) or 1copy of 800 Words (English).

注意 : 論文要旨は、東工大リサーチリポジトリ (T2R2) にてインターネット公表されますので、公表可能な範囲の内容で作成してください。

Attention: Thesis Summary will be published on Tokyo Tech Research Repository Website (T2R2).