T2R2 東京工業大学リサーチリポジトリ Tokyo Tech Research Repository

# 論文 / 著書情報 Article / Book Information

題目(和文)			
Title(English)	Flexural and Shear Performance of Steel-encased Precast Spun Concrete Piles		
著者(和文)	Thusoo Shreya		
Author(English)	Shreya Thusoo		
出典(和文)	学位:博士(学術), 学位授与機関:東京工業大学, 報告番号:甲第11662号, 授与年月日:2020年9月25日, 学位の種別:課程博士, 審査員:WIJEYEWICKREMA ANIL,河野 進,岩波 光保,竹村 次朗,佐々木 栄一		
Citation(English)	Degree:Doctor (Academic), Conferring organization: Tokyo Institute of Technology, Report number:甲第11662号, Conferred date:2020/9/25, Degree Type:Course doctor, Examiner:,,,,		
学位種別(和文)			
Category(English)	Doctoral Thesis		
種別(和文)			
Type(English)	Summary		

## 論文要旨

#### THESIS SUMMARY

系・コース: Department of, Graduate major in	Civil and Environmental Engineering Civil Engineering コー	申請学位(専攻分野): Academic Degree Requested	博士 <sub>Doctar of</sub> (Philosophy)
学生氏名:	Thusso Shrova	指導教員(主):	Associate Prof. Anil C.
Student's Name	Thusoo Shreya	Academic Supervisor(main)	Wijeyewickrema
		指導教員(副):	Drof Susanny Kono
		Academic Supervisor(sub)	Froi. Susumu Kono

### 要旨(英文800語程度)

#### Thesis Summary (approx.800 English Words )

The thesis presents a comprehensive study on the flexural and shear performance of steel-encased precast spun concrete (SC) piles using large-scale experimental data and analytical modeling. The research mainly focuses on the assimilation of experimental data, improvement of currently available flexural and shear design guidelines, and development of numerical models to simulate the flexural behavior of SC piles. The results from this study are valuable and useful for engineers designing foundations in areas with high seismicity.

The study first focuses on analyzing the test data from previous experiments on 11 SC pile specimens to investigate the bending moment capacity, damage process, and failure criteria for flexural failure. The main parameters include the axial load ratio (0-0.35), steel casing thickness (4.5-6.0 mm), concrete layer thickness (50-68 mm), and filling material (hollow, cement paste, concrete). The test results show that concrete crushing and local buckling of steel are the major factors influencing the bending capacity of SC piles, given that global buckling is not permitted. The damage at failure state is characterized by local buckling of steel between 0-100 mm, concrete crushing at the outer layer of concrete between 0-120 mm, and spalling at the inner layer of concrete between 0-240 mm, all from the base. High curvature demands are seen to be concentrated between 0-125 mm from the base for drift ratios less than 1.5%. Further, it is observed that governing factor changes from concrete crushing to steel local buckling with an increase in axial load or reduction in steel to concrete strength ratio. It is found that filling the core with a low-cost, low-strength material prevents the spalling of the inner line of concrete and, consequently, increases the drift and ductility performance.

The applicability of stress distribution-based methods given in available guidelines by AIJ (2008), Eurocode 4 (2004), and ANSI/AISC 360-16 (2016) for bending capacity of columns/composite members under axial-flexural loads is investigated. The applicability of strain compatibility-based method in the draft guidelines for SC piles by the AIJ (2020) committee is also examined. For this purpose, a database of 79 bending tests on SC piles, including tests from literature and pile manufacturers in Japan, is organized. The scope of the dataset is defined by characteristic parameters, axial load ratio (-0.4-0.5), section slenderness ratio (36-133), member slenderness ratio (6.0-18.8), concrete compressive strength (81-123 MPa) and steel tensile strength (301-521 MPa). Modifications are proposed to the drafted guidelines for SC piles to give conservative predictions with an error of less than 20% for all tests in the database.

The development of a fiber-based finite element model of SC piles is carried out to simulate the moment-drift behavior under axial-flexural loads up to and beyond the peak response. The model is characterized by a single beam-column element in the damage zone at the base. The stress-strain relationship of fiber elements of steel in the damage zone follows a pipe buckling model. For this, a hysteretic model for steel is developed with a linear falling branch and a constant stress branch after initiation of buckling. The fiber elements of steel in the low damage zone do not undergo buckling. The enhancement of concrete strength due to confinement by steel casing is considered by using a confined concrete model such that the reduction in confinement due to the hollow core is also taken onto account. The sectional behavior is validated by comparison with the moment-curvature responses from five simply supported bending tests covering axial load ratios of -0.4 to 0.5 times the section capacity. Whereas the member behavior is validated by comparison with the moment-drift responses from thirteen tests covering simply supported and cantilevered bending tests, hollow and filled-core specimens, and axial load ratios of -0.4 to 0.5 times the section capacity. It is found that the model can simulate the flexural behavior of SC piles for axial load ratios of 0 to 0.5 with good accuracy.

Furthermore, to investigate the performance of SC piles under shear loads, shear tests on 400 diameter SC piles were conducted with the axial load ratio as the main parameter. The objective of these tests is to gather experimental data on the shear behavior of SC piles to investigate the shear capacity, damage process, and failure criteria for shear failure. For the case of SC pile with high compression axial load ratio of 0.5 and shear span to diameter ratio of 0.5, a brittle shear force vs. drift response and shear failure is reported, accompanied by the sudden loss of axial capacity to half of the initial value. From the extent of shear yielding along the cross-section, 1/2 of the area of steel is found to be effective in resisting shear at the failure. Additionally, it is confirmed that the design of SC piles is governed by the bending capacity rather than the shear capacity in most design situations.

備考: 論文要旨は、和文 2000 字と英文 300 語を1部ずつ提出するか、もしくは英文 800 語を1部提出してください。

Note : Thesis Summary should be submitted in either a copy of 2000 Japanese Characters and 300 Words (English) or 1copy of 800 Words (English).

注意:論文要旨は、東工大リサーチリポジトリ(T2R2)にてインターネット公表されますので、公表可能な範囲の内容で作成してください。 Attention: Thesis Summary will be published on Tokyo Tech Research Repository Website (T2R2).