

論文 / 著書情報
Article / Book Information

題目(和文)	Dion-Jacobson型層状ペロブスカイトにおける酸化物イオン伝導
Title(English)	Oxide-Ion Conduction in the Dion-Jacobson-Type Layered Perovskites
著者(和文)	張文銳
Author(English)	Wenrui Zhang
出典(和文)	学位:博士(理学), 学位授与機関:東京工業大学, 報告番号:甲第11379号, 授与年月日:2020年3月26日, 学位の種別:課程博士, 審査員:八島 正知,河野 正規,植草 秀裕,沖本 洋一,前田 和彦
Citation(English)	Degree:Doctor (Science), Conferring organization: Tokyo Institute of Technology, Report number:甲第11379号, Conferred date:2020/3/26, Degree Type:Course doctor, Examiner:,,,,
学位種別(和文)	博士論文
Category(English)	Doctoral Thesis
種別(和文)	審査の要旨
Type(English)	Exam Summary

(博士課程)

論文審査の要旨及び審査員

報告番号	甲第	号	学位申請者氏名	ZHANG WENRUI		
論文審査 審査員		氏名	職名		氏名	職名
	主査	八島 正知	教授		前田 和彦	准教授
	審査員	河野 正規	教授	審査員		
		植草 秀裕	准教授			
沖本 洋一		准教授				

論文審査の要旨 (2000 字程度)

Materials exhibiting high oxide-ion conductivities have numerous applications in various electrochemical devices, such as solid-oxide fuel cells (SOFCs), separation membranes and gas sensors. Since the high oxide-ion conductivities are achieved in a limited number of structure families, the discovery of oxide-ion conductors with new crystal structures is of vital importance for the development of their applications. In this doctoral thesis, the Dion–Jacobson-type layered perovskites have been found as a new structure family of oxide ion conductors, through the screening by bond valence-based-energy calculations, synthesis, electrochemical measurements, thermogravimetric analyses, and the crystal structure analyses using the high-temperature neutron and synchrotron X-ray diffraction data. $\text{CsBi}_2\text{Ti}_2\text{NbO}_{10-\delta}$ was found to be the first example of the Dion–Jacobson-type oxide-ion conductor where δ represents the oxygen-vacancy content. $\text{CsBi}_2\text{Ti}_2\text{NbO}_{10-\delta}$ showed higher bulk oxide-ion conductivities than those of other widely known oxide-ion conductors such as the conventional yttria-stabilized zirconia (YSZ) and $\text{Na}_{0.5}\text{Bi}_{0.5}\text{TiO}_3$. The oxide-ion conduction was also confirmed in other compositions of the Dion–Jacobson-type layered perovskites. The thesis, entitled “Oxide-Ion Conduction in the Dion–Jacobson-Type Layered Perovskites,” consists of the following four chapters.

In chapter 1, entitled “Introduction,” the background and purpose of this study were explained. First of all, the importance of the research of oxide-ion conductors was described. Secondary, previous researches on the oxide-ion conducting perovskite and perovskite related oxides in the literature were reviewed. Problems of the previous researches and unresolved issues were pointed out. The experimental and calculation methods used in this thesis were also introduced. Mother materials $\text{CsBi}_2\text{Ti}_2\text{NbO}_{10}$ and $\text{CsR}_2\text{Ti}_2\text{NbO}_{10}$ (R = rare earth) were selected, because the bond-valence-based energy barriers for the oxide-ion migration, E_b , were relatively low in the screening of 69 Dion–Jacobson-type layered perovskites.

In chapter 2, entitled “Dion–Jacobson-type $\text{CsBi}_2\text{Ti}_2\text{NbO}_{10}$ -based Materials as Oxide-Ion Conductors,” the title compounds were synthesized by the solid-state-reaction method and the crystal structure of $\text{CsBi}_2\text{Ti}_2\text{NbO}_{10-\delta}$ was analyzed using high-temperature neutron and synchrotron X-ray diffraction data. The Rietveld refinements of $\text{CsBi}_2\text{Ti}_2\text{NbO}_{10-\delta}$ were successfully performed using a single orthorhombic *Ima2* structure at 297–813 K and a single tetragonal *P4/mmm* structure at 833–1073 K on heating, showing an orthorhombic-to-tetragonal (o-to-t) phase transition. The presence of oxygen vacancies was confirmed from both the refined occupancy factors of oxygen atoms using variable temperature neutron-diffraction data and the weight loss observed by the thermogravimetric analysis. The existence of oxygen vacancies was responsible for the high oxide-ion conductivities of tetragonal $\text{CsBi}_2\text{Ti}_2\text{NbO}_{10-\delta}$. Electrical conductivities were measured by AC impedance

spectroscopy method and by DC 4-probe method in flowing dry air, N₂ and O₂ gases, respectively. The bulk conductivity of CsBi₂Ti₂NbO_{10-δ} was 8.9 × 10⁻² S cm⁻¹ at 1073 K. The conductivity abruptly increased between 823 and 873 K on heating, which was attributed to the increase of oxygen vacancy concentration and the o-to-t phase transition. Oxygen concentration-cell measurements were performed to estimate the oxide-ion transport number t_{ion} in CsBi₂Ti₂NbO_{10-δ}. The t_{ion} values were 1.00–0.98 between 873 and 1173 K in air/O₂, 0.97–0.95 between 873 and 1173 K in air/N₂, and 0.87 at 873 K in air/5% H₂ in N₂. The bond valence-based energy landscape and neutron scattering length density distribution were used to investigate possible oxide-ion migration paths. The results indicated two-dimensional oxide-ion migration paths along the edges of the octahedron in the oxide-ion conducting inner perovskite layer. A new concept “large bottlenecks for oxide-ion migration by large size of Cs⁺ and Bi³⁺ displacement” was proposed to explain the high oxide-ion conductivity of the Dion–Jacobson-type layered perovskite CsBi₂Ti₂NbO_{10-δ}. The oxide-ion conductivity was increased by partial aliovalent cation substitutions for the mother material CsBi₂Ti₂NbO_{10-δ}.

In chapter 3, entitled “Dion–Jacobson-type CsR₂Ti₂NbO₁₀-based Materials as Oxide-Ion Conductors (*R* = Rare earth),” the title compounds were synthesized and their electrical conductivities were measured by DC 4-probe method. CsLa₂Ti₂NbO_{10-δ} was selected for further study because it showed highest electrical conductivity among the successfully synthesized CsR₂Ti₂NbO₁₀ compounds. The oxide-ion conductivity of CsLa₂Ti₂NbO_{10-δ} was 1.89 × 10⁻⁴ S cm⁻¹ at 1273 K in air. The t_{ion} estimated using an oxygen concentration cell of CsLa₂Ti₂NbO_{10-δ} indicated that the dominant charge carrier in CsLa₂Ti₂NbO_{10-δ} was oxide ion. The Rietveld analyses of variable-temperature neutron and synchrotron X-ray diffraction data of CsLa₂Ti₂NbO_{10-δ} were successfully performed by the tetragonal *I4/mmm* Dion-Jacobson-type structure from room temperature to 1073 K, revealing no phase transition in this temperature range. The bond valence-based energy landscape was used to investigate possible oxide-ion migration path and energy barrier for oxide-ion migration. The landscape showed two-dimensional oxide-ion diffusion along the edges of octahedron in the perovskite layers of CsLa₂Ti₂NbO_{10-δ}. The electrical conductivity was increased by doping for the mother material CsLa₂Ti₂NbO_{10-δ}.

In chapter 4, entitled “Conclusion and Future Work,” the results and discussion of this thesis were summarized. The conclusion and impact of this thesis were described. Some future works were proposed on the basis of the results presented in this doctoral thesis.

The present finding of the new structure family of oxide-ion conductors in this doctoral thesis would offer new routes for the design of novel oxide-ion conductors based on the Dion–Jacobson-type layered perovskites and then improve the developments in chemistry, physics, and materials science.

注意：「論文審査の要旨及び審査員」は、東工大リサーチポジトリ(T2R2)にてインターネット公表されますので、公表可能な範囲の内容で作成してください。